- (d) Optional substances as provided in paragraph (a) of this section include:
- (1) Substances generally recognized as safe in food.
- (2) Substances subject to prior sanction or approval for uses with a copolymer of vinyl acetate and crotonic acid and used in accordance with such sanction or approval.
- (3) Substances identified in this subparagraph and subject to such limitations as are provided:

List of substances	Limitations
Silica. Japan wax.	

- (e) Copolymer of vinyl acetate and crotonic acid used as a coating or as a component of a coating conforming with the specifications of paragraph (e)(1) of this section are used as provided in paragraph (e)(2) of this section.
- (1) Specifications. (i) The chloroform-soluble portion of the water extractives of the coated film obtained with distilled water at 120 °F for 24 hours does not exceed 0.5 milligram per square inch of coated surface.
- (ii) The chloroform-soluble portion of the n-heptane extractives of the coated film obtained with n-heptane at 70 °F for 30 minutes does not exceed 0.5 milligram per square inch of coated surface.
- (2) Conditions of use. The copolymer of vinyl acetate and crotonic acid is used as a coating or as a component of a coating for polyolefin films for packaging bakery products and confectionery.

§ 175.360 Vinylidene chloride copolymer coatings for nylon film.

Vinylidene chloride copolymer coatings identified in this section and applied on nylon film may be safely used as food-contact surfaces, in accordance with the following prescribed conditions:

- (a) The coating is applied as a continuous film over one or both sides of a base film produced from nylon resins complying with §177.1500 of this chapter.
- (b) The coatings are prepared from vinylidene chloride copolymers produced by copolymerizing vinylidene chloride with one or more of the monomers acrylic acid, acrylonitrile, ethyl

- acrylate, methacrylic acid, methyl acrylate, methyl methacrylate (CAS Reg. No. 80-62-6; maximum use level 6 weight percent) and 2-sulfoethyl methacrylate (CAS Reg. No. 10595-80-9; maximum use level 1 weight percent). The finished copolymers contain at least 50 weight percent of polymer units derived from vinylidene chloride. The finished coating produced from vinylidene chloride copolymers produced by copolymerizing vinylidene chloride with methyl methacrylate and/or sulfoethyl methacrylate, or with methyl methacrylate and/or 2-sulfoethyl methacrylate together with one or more of the other monomers from this section, is restricted to use at or below room temperature.
- (c) Optional adjuvant substances employed in the production of the coatings or added thereto to impart desired properties may include sodium dodecylbenzenesulfonate.
- (d) The coating in the finished form in which it is to contact food, when extracted with the solvent or solvents characterizing the type of food, and under conditions of time and temperature characterizing the conditions of its intended use as determined from tables 1 and 2 of §176.170(c) of this chapter, shall yield net chloroform-soluble extractives not to exceed 0.5 milligram per square inch of coated surface when tested by the methods described in §176.170(d) of this chapter.
- (e) Acrylonitrile copolymers identified in this section shall comply with the provisions of §180.22 of this chapter

[42 FR 14534, Mar. 15, 1977, as amended at 43 FR 7206, Feb. 21, 1978; 45 FR 76998, Nov. 21, 1980; 47 FR 54430, Dec. 3, 1982]

§ 175.365 Vinylidene chloride copolymer coatings for polycarbonate film.

Vinylidene chloride copolymer coatings identified in this section and applied on polycarbonate film may be safely used as food-contact surfaces, in accordance with the following prescribed conditions:

(a) The coating is applied as a continuous film over one or both sides of a base film produced from polycarbonate resins complying with §177.1580 of this chapter.